

Flexlight Advanced 1502 S2





Flexlight Advanced 1502 S2



Main applications

- Covered outdoors
- Sport hall roofs
- Shading structures

Major advantages

- Long lasting and low maintenance
- Controled color per translucency (VISU service)
- High dimensional stability due to Précontraint® technology

Technical specifications	Standards
S2 PVDF / PVDF	
High tenacity Polyester 1670/2200 Dtex Low wick treatment for anticapillarity	
1500 g/m ²	EN ISO 2286-2
180 cm	
-Physical properties	EN ISO 1421
	DIN 53.363
15 daN/5 cm	EN ISO 2411
alues with +/5% tolerance	
Flame retardancy	
C-s2,d0	EN 13501-1 DIN 4102-1
- Ы	DIN 4102-1
Thickness and dimensional stability	
1.14 mm	
<1.2%/<1.2%	EN 15977
< 0.5% / < 0.5%	EN 15977
Thermal and acoustic performances	
U=5.6/6.4W/sqm/°C	Calculated
16 dBA	ISO 140-3 & ISO 717-1
Solar optical values	
7 %	NFP 38511
3 %	EN 410
89%	
4%	
81%	EN 410
8%	
0%	
90.1%	ASTM E1980-01 (approach II)
Certifications, labels, guarantees, recycling	
	S2 PVDF / PVDF High tenacity Polyester 1670/2200 Dtex Low wick treatment for anticapillarity 1500 g/m² 180 cm Physical properties 1000 / 800 daN / 5 cm 15 daN / 5 cm 15 daN / 5 cm 15 daN / 5 cm Thickness and dimensional stability 1.14 mm <1.2% / <1.2% <0.5% / <0.5% Thermal and acoustic performances U = 5.6 / 6.4 W / sqm / ° C 16 dBA Solar optical values 7 % 3 % 89% 4% 81% 886 0% 90.1%

ISO 9001	Precontraint	15-year	CSR and LEED reports
ISO 14001	technology	warranty	available on request

the buyer of our products is fully response for their application and their transformation with regard to any possible third party. The buyer of our products is responsible for their implementation and installation according to the standards, work manship and safety regulations in force in destination countries. For information on our contractual warranty, please referto the relevant terms and conditions. The values quoted above represent results of tests performed in compliance with common design practices and are provided for information only to enable customers to make the best use of our products. Our products are subject to changes based on technical advances and we reserve the right to modify their characteristics at anytime. The buyer of our products is responsible for checking the validity of the above data.







