
Serge Ferrari
industries

Protect


Mesh 360-362

Précontraint®







White 360-1066*
362-8100




Green 360-50201*
362-50201



Grey 360-1070*
362-1070



Black 360-1075*
362-1075



Light ivory 360-1076*
362-1076

* Colors subject to MOQ & specific lead time

Protect
Mesh 360 - 362

Mesh with low opening factor suitable for agricultural & industrial applications

Main advantages

- Exceptional dimensional stability thanks to Precontraint® technology
- UV resistant and long lasting
- High resistance to wind & deformation

Main applications

- Pool cover / air filtration
- Winbreak building facade
- Agricultural stabulations
- Partition, shading, fences
- Masquing equipments

	Protect Mesh	
	360	**362**
	Technical specifications	
Support cloth DIN 60001	1,100 dtex PES HT	
Coating	PVC	
Finish	Acrylic varnish	
Weight EN ISO 2286-2	430 g/m² • 12.7 oz/sq. yd	
Width	267 cm • 105.1 in	
Standard format length	±50 lm/±300 lm • ±54.68 yd/±328.08 yd	
	Physical properties	
Tensile strength (warp/weft) EN ISO 1421	250/270 daN/5 cm • 562/607 lbs/2 in	
Tear strength (warp/weft) DIN 53.363	50/50 daN • 112/112 lbs	
Openess factor	28%	
Permeability to air* NF EN ISO 9237	2.488 l/dm²/min	
Temperature resistance DIN EN 1876-1	-30°C/+70°C • -22°F/+158°F	
	Fire resistance	
Rating - International fire certificate available, such as**	–	**B1/**DIN 4102-1 **M2/**NF P 92-507 NFPA 701 Method 2
	Environmental properties	
Carbon impact EN 15804 + A2***	–	3.07 Kg CO_2 eq/m²
	Managment systems	
	Quality: ISO 9001 • **Environment**: ISO 14001 • **Energy**: ISO 50001	
	Certifications, labels	

Précontraint® Technology

* Test surface 20 cm², pressure 200 Pa
** Contact us for latest certificate updates & validities
*** External 3d party verification

[1] Summarizes the group's CSR project focused on human, to align economic performance and positive impact.

Quoted technical characteristics are average values subject to +/-10% tolerance.

The buyer of our products is fully responsible for their application and their transformation with regard to any possible third party. The buyer of our products is responsible for their implementation and installation according to the standards, wormanship and safety regulations in force in destination countries. For information on our contractual warranty, please refer to the relevant terms and conditions. The values quoted above represent results of tests performed in compliance with common design practices and are provided for information only to enable customers to make the best use of our products. Our products are subject to changes based on technical advances and we reserve the right to modify their characteristics at any time. The buyer of our products is responsible for checking the validity of the above data.

The colours and textures represented are provided as reference only.

Serge Ferrari group

BUITINK TECHNOLOGY Advanced Lightweight Structures

sergeferrarigroup.com

Précontraint is a Serge Ferrari SAS registered trademark.
Ref CT-02566 • 08/2026 • PDF ONLY

EN

Photo credits: ©SergeFerrari